

## ALUMINIO 6061

### ANALISIS QUIMICO

Al	Mg	Si	Fe	Cu	Zn	Ti	Mn	Cr	Otros
Balance	0.8% - 1.2%	0.4% - 0.8%	0.7% max	0.15% - 0.40%	0.25% max	0.15% max	0.15% max	0.04% - 0.35%	0.05%

