

ALUMINIO 6063

ANALISIS QUIMICO

Al	Mg	Si	Fe	Cu	Zn	Ti	Mn	Cr
Balance	0.45% - 0.9%	0.2% - 0.6%	0.0% - 0.35%	0.0% - 0.10%	0.0% - 0.10%	0.0% - 0.10%	0.0% - 0.10%	0.10% max