

BRONCE SAE 62

ANALISIS QUIMICO

Cobre	Estaño	Plomo	Zinc	Niquel
86% - 89%	9% - 11%	0% -0.30%	1% - 3%	0% - 1%