

# BRONCE SAE 64

## ANALISIS QUIMICO

Cobre	Estaño	Plomo	Zinc	Niquel
78% - 82%	9% - 11%	9% - 11%	0% - 0.75%	0% - 0.75%

