

BRONCE SAE 65

ANALISIS QUIMICO

Cobre	Estaño	Antimonio	Fierro	Aluminio	Plomo	Zinc	Niquel	Fosforo	Silicio	Azufre
88% - 90%	10% - 12%	0% -0.020%	0% - 0.015%	0% - 0.005%	0% - 0.50%	0% - 0.50%	0% - 0.50%	0% - 0.30%	0% - 0.005%	0% - 0.005%

